LECTURE 5

Main Methods of Obtaining Binders

Polymerization Kinetics, Polycondensation Pathways, Sol-Gel Synthesis, and Industrial Reactor Engineering

Lecture: acc.professor Kudaibergenova Bates Malikovna.

Lecture Overview: Plan, Aim & Key Tasks

Lecture Plan

1. Radical Methods: Addition polymerization (bulk, emulsion)

2. Step-Growth: Polycondensation & ring-opening

3. Sol-Gel Routes: Inorganic & hybrid network formation

4. Modification: Polymer-analogous transformations

5. Bio-Extraction: Isolation & refining of natural binders

Lecture Aim

To examine the fundamental chemical reaction mechanisms, industrial synthesis pathways, rheological controls, and technological parameters involved in producing synthetic, inorganic, and bio-derived polymer binders.

Key Learning Tasks

Compare: Chain-growth vs. step-growth kinetics

Analyze: Epoxy & polyurethane synthesis

Evaluate: Sol-gel hydrolysis & condensation

Identify: Green extraction of bio-polymers

Fundamental Concept: The chosen synthesis route directly governs binder molecular weight distribution, crosslink density, purity, and processing viscosity.

Synthesis Methodology Classification

Binder production spans chemical synthesis, inorganic network formation, physical refining, and post-polymerization modification.

Chain-Growth Addition

Rapid unsaturated monomer addition via radical, ionic, or coordination catalysis without byproducts.

Step-Growth Polycondensation

Stepwise condensation between difunctional monomers with elimination of small molecules (H2O, HCl, ROH).

Sol-Gel Inorganic Chemistry

Hydrolysis and condensation of metal alkoxides creating inorganic/hybrid siloxane matrix networks.



Selection Criterion: Monomer functional group reactivity, exotherm control, and target resin purity.

Free-Radical Polymerization Synthesis

Reaction Stages

1. Initiation: Thermal/photolytic homolytic cleavage of peroxides (BPO) or azo compounds (AIBN) into primary radicals (R•).

2. Propagation: Addition of radical to vinyl monomer carbon-carbon double bonds (k_p).

3. Termination: Radical coupling or disproportionation (k_t).

Polymer Kinetic Rate (R_p)

Governed by monomer concentration [M] and initiator concentration [I]:

$$R_p = k_p \cdot [M] \cdot (f \cdot k_d \cdot [I] / k_t)^{0.5}$$

Industrial Binders: Acrylics (PMMA), Polystyrene, Vinyl Acetate, and Fluoropolymers.

Bulk (Mass) Polymerization Technique

Pure Monomer Reaction Environment

Carried out by dissolving initiator directly in neat liquid monomer without solvents or dispersing media. Yields highest optical purity resin binders.

> **Trommsdorff-Norrish Effect (Auto-acceleration)**
> Viscosity rise restricts radical diffusion (lowering k_t) while small monomers continue diffusing (k_p stays high), causing explosive exotherms.

Solution Polymerization Synthesis

Process Architecture

Viscosity Control: Prevents auto-acceleration by maintaining low fluid viscosity.
Monomers and initiators are dissolved in a compatible organic solvent or water. Solvent acts as a thermal heat sink, moderating reaction exotherms.

Solvent Chain Transfer

Equation: Mayo equation models degree of polymerization vs. [Solvent]/[Monomer].
Radicals can abstract atoms from solvent molecules (C_S), limiting the maximum achievable molecular weight (M_n).

Direct Binder Utility: Produced solution can be directly applied as varnish, coating, or liquid matrix resin.

Heterogeneous Routes: Suspension & Emulsion

Suspension Polymerization

Droplet Size: 10 µm – 5 mm

• Monomer droplets suspended in water by mechanical agitation + protective colloids (PVA).

• Monomer-soluble initiator acts in mini bulk reactors.

• Yields spherical resin beads ideal for ion-exchange matrices.

Emulsion Polymerization

Particle Size: 50 – 300 nm

• Surfactant forms water-insoluble micelles; water-soluble initiator (KPS) initiates in aqueous phase.

• Harkins-Smith-Ewart kinetic model (high rate + high M_w).

• Produces waterborne latex binders and bio-adhesive emulsions.

Environmental Impact: Emulsion synthesis eliminates volatile organic compound (VOC) emissions.

Polycondensation (Step-Growth) Synthesis

Stepwise Condensation Dynamics

Any two functionalized molecules in the reactor can react. High molecular weight is only attained at extremely high conversion degrees (p > 0.99).

Carothers Equation

$$X_n = 1 / (1 - p)$$

Where X_n is number-average degree of polymerization and p is fractional monomer conversion.



Stoichiometric Imbalance (r)

$$X_n = (1 + r) / (1 + r - 2rp)$$

Slight excess of one functional group caps final molecular weight.

Key Resins: Polyesters, Polyamides, Phenolic Novolacs, and Polyimides.

Synthesis of Epoxy Binders: DGEBA Pathway

Two-Step Reaction Sequence

Step 1: Nucleophilic Addition: Bisphenol A reacts with excess Epichlorohydrin catalyzed by alkali (NaOH) to yield chlorohydrin intermediate.

Step 2: Dehydrohalogenation: Ring closure driven by base releases NaCl salt byproduct, yielding diglycidyl ether terminal oxirane groups.

Molar Ratio Control

Purification: Salt washing & vacuum distillation of unreacted epichlorohydrin.

High excess of Epichlorohydrin (10:1 ratio) favors n = 0 liquid DGEBA monomer (MW ≈ 340 g/mol, viscosity ≈ 12 Pa·s). Lower ratios yield solid oligomeric epoxies.

Epoxidized Novolacs: Phenol-formaldehyde novolacs epoxidized to yield high-functionality (>3 oxiranes/molecule) resins.

Synthesis of Polyurethane (PU) Binders

Polyaddition without Byproduct Formation

Synthesized by reacting polyisocyanates (MDI, TDI, HDI) containing active -N=C=O groups with polyols (polyester or polyether diols) containing active hydroxyl (-OH) groups.

Prepolymer Synthetic Technique

Isocyanate-terminated prepolymers prepared first (NCO/OH > 2), then chain-extended with short diols (1,4-butanediol) for microphase-separated hard/soft domains.

Catalysts: Organometallic compounds (Dibutyltin dilaurate - DBTDL) or tertiary amines (DABCO).

Ring-Opening Polymerization (ROP)

Thermodynamic Driving Force

No Volatiles: Proceeds without byproduct elimination, preventing void formation.
Relief of ring strain (enthalpic gain, $\Delta H < 0$) drives the polymerization of cyclic esters, lactones, lactams, and cyclic siloxanes into linear high-molecular-weight chains.

Synthetic Applications

Lactide → PLA: Tin(II) 2-ethylhexanoate (Sn(Oct)2) catalyzed ROP of L-lactide.

Caprolactone → PCL: Coordination-insertion ROP for biodegradable matrices.

CBT → PBT: Low-viscosity cyclic oligomer ROP inside RTM molds.

Living Polymerization: Enables precise block copolymer architecture control (dispersity $M_w/M_n < 1.1$).

Sol-Gel Method for Inorganic & Hybrid Binders

1. Alkoxide Precursors

Tetraethyl orthosilicate (TEOS), Tetramethyl orthosilicate (TMOS), or organosilanes (APTES, MAPTMS).

2. Hydrolysis Reaction

Alkoxy (-OR) groups replaced by hydroxyl (-OH) silanols via acid (HCl) or base (NH3) catalysis.

3. Polycondensation Gelation

Silanols condense into 3D crosslinked siloxane (Si-O-Si) inorganic networks entrapping liquid phase.

Organo-Silica Hybrids (ORMOCERs): Organically modified silanes incorporate reactive vinyl/epoxy groups directly into the inorganic backbone.

Polymer-Analogous Transformations

Chemical Functionalization of Pre-formed Chains

Modifying functional groups attached to pre-existing macromolecular backbones without altering the degree of polymerization.

Polyvinyl Alcohol (PVA) Hydrolysis
PVA cannot be synthesized from vinyl alcohol monomer; produced by alkaline alcoholysis of polyvinyl acetate.

Maleic Anhydride Grafting (MAH-g-PP)
Reactive extrusion grafting of maleic anhydride onto polyolefins to create polar binding sites.

Industrial Utility: Converting non-polar commodity polymers into high-adhesion functional matrices.

Extraction & Refining of Bio-Binders

Chitosan Deacetylation

Degree of Deacetylation (DDA): Must exceed 75% for acid solubility and binder utility.
Extracted chitin from crustacean shells undergoes heterogeneous alkaline deacetylation (40–50% NaOH at 100–120°C) to convert acetamido groups to free amino (-NH2) groups.

Lignin Kraft Isolation

Refining: Solvent fractionation yields narrow polydispersity bio-phenolic precursors.
Black liquor from sulfate pulping acidified with CO2/H2SO4 to precipitate technical Kraft lignin rich in phenolic hydroxyl groups for resin synthesis.

Green Extraction: Supercritical CO2 and ionic liquids replace hazardous organic solvents in bio-binder isolation.

Molecular Weight & Dispersity (Đ) Control

Polydispersity Index (Đ = M_w / M_n)

The ratio of weight-average (M_w) to number-average (M_n) molecular weight dictates the breadth of matrix melt processing temperatures and melt elasticity.

Free Radical Polymerization: Đ ≈ 1.5 - 2.0
Broad distribution providing melt strength during extrusion blowing.

Controlled Radical (RAFT / ATRP): Đ ≈ 1.05 - 1.20
Ultra-narrow distribution yielding low melt viscosity for composite infusion.

Viscosity Correlation: Zero-shear melt viscosity scales with molecular weight as $\eta_0 \propto (M_w)^{3.4}$.

Industrial Polymerization Reactor Systems

CSTR (Stirred-Tank)

Continuous Stirred-Tank Reactor. Provides uniform temperature control and steady-state concentration profiles for solution binder production.

Tubular / Plug-Flow

High surface area-to-volume ratio enables rapid heat transfer for high-pressure polymerization (e.g., LDPE autoclaves/tubulars).

Reactive Extruders

Twin-screw extruders act as continuous high-viscosity reactors for polyaddition, functional grafting, and solvent-free processing.

Heat Removal Challenge: Polymerization reactions release 50–100 kJ per mole of converted double bond; requires internal cooling coils or jacketed cooling.

Catalyst Systems in Binder Synthesis

Ziegler-Natta & Metallocenes

Impact: Governs binder crystallinity, melting point, and mechanical modulus.
Coordination catalysts (TiCl4/AlEt3 or single-site Zr metallocenes) control polyolefin stereoregularity (isotactic vs. syndiotactic PP).

Organocatalysis & Enzymes

Biomedical Advantage: Zero toxic heavy metal residues in medical grade polymers.
N-heterocyclic carbenes (NHCs) or lipase enzymes (Candida antarctica) catalyze polycondensation under ultra-mild, metal-free conditions.

Turnover Frequency (TOF): High catalyst activity permits sub-ppm loading levels.

In-Line Monitoring & Conversion Control

NIR Spectroscopy

Near-Infrared fiber optic probes track vinyl C=H overtone absorption decrease in real-time during polymerization.

In-Line Viscometry

Torsional quartz viscometers measure viscosity build-up to signal precise reaction quench timing.

Refractometry

Refractive index shifts correlate directly with monomer-to-polymer conversion percentage.

Target Purity: Residual monomer stripping via thin-film evaporators must reduce unreacted species to <0.1 wt%.

Purification & Volatile Stripping Techniques

Devolatilization Operations

Post-polymerization removal of unreacted monomer, solvent traces, and reaction water to eliminate void formation during composite curing.

> **Wiped-Film Evaporator (WFE)**
> Rotating blades spread polymer melt into thin films (0.1–1 mm) under deep vacuum (<1 mbar) and elevated heat.

Prepreg Quality Impact: Residual solvents cause internal delamination voids during autoclave curing.

Synthesis Route Comparison Matrix

Bulk Route

Purity: Exceptional

Rate: Fast / Explosive

Heat Control: Very Difficult

Solution Route

Purity: Solvent Dependent

Rate: Moderate

Heat Control: Excellent

Emulsion Route

Purity: Contains Surfactants

Rate: Very Fast

Heat Control: Excellent

Process Selection Rule: Choose solution/emulsion for coatings and adhesives; bulk/polycondensation for structural composite matrices.

Green Synthesis & Sustainable Production

Atom Economy & Solvent-Free Reactions

Example: Polyurethane polyaddition exhibits 100% theoretical atom economy.
Designing synthetic routes where all raw material atoms are incorporated into the final polymer binder without producing waste byproducts.

Bio-Based Feedstock Substitution

Outcome: Reduced lifecycle carbon intensity and net zero VOC emissions.
Replacing petroleum-derived Bisphenol A with bio-based monomers like isosorbide, vanillin, or cardanol derived from cashew nut shell liquid.

Energy Efficiency: Microwave-assisted synthesis accelerates condensation reactions by 10x to 100x.

Industrial Scale-Up Engineering Challenges

Heat Transfer Limitations

Reactor volume scales as r^3 while cooling surface area scales as r^2, causing dangerous exotherm accumulation in large tanks.

Mixing & Mass Transfer

High fluid viscosity inhibits monomer diffusion, broadening molecular weight distribution and creating unreacted dead zones.

Batch-to-Batch Uniformity

Minor variations in raw material moisture or catalyst purity alter gelation time and final crosslink density.

Engineering Solution: Computational Fluid Dynamics (CFD) modeling of agitator impeller shear patterns during scale-up.

Future Horizons: Continuous Microfluidic Synthesis

Continuous Flow Microreactors

Synthesizing binders inside microfluidic channels (<1 mm diameter) offers near-infinite heat transfer rates, precise residence time control, and ultra-narrow dispersity.

Automated High-Throughput: AI-guided robotic synthesis screening thousands of binder formulations daily.

Photo-Flow Chemistry: Rapid UV polymerization in transparent capillary microreactors.

On-Demand Production: Modular binder synthesis units deployed directly at composite manufacturing sites.

Technology Transition: Shifting from 10,000-liter batch kettles to continuous flow micro-factory arrays.

Summary: Key Binder Obtaining Methods

01

Chain-Growth Addition

Radical, ionic, or emulsion routes for vinyl, acrylic, and fluoro-binder resins without byproducts.

02

Step-Growth Condensation

High-conversion synthesis yielding epoxies, polyurethanes, polyesters, and polyimide matrices.

03

Sol-Gel & Bio-Refining

Inorganic siloxane hydrolysis alongside alkaline extraction of chitosan and lignin biopolymers.

Core Takeaway: Mastering synthesis kinetics and reactor engineering is essential to tailor polymer binder structure for advanced composite performance.

Thank You for Your Attention

acc.professor Kudaibergenova Bates Malikovna.