LECTURE 4

Main Types of Binders Used in Medicine and Requirements for Them

Biocompatibility Criteria, Biodegradation Control, Synthetic & Natural Polymer Matrices

Lecture: acc.professor Kudaibergenova Bates Malikovna.

Lecture Overview: Plan, Aim & Key Tasks

Lecture Plan

1. Standards: ISO 10993 & biocompatibility rules

2. Natural Binders: Collagen, gelatin, chitosan & alginate

3. Synthetic Resins: PLA, PGA, PLGA, PCL & PMMA

4. Hydrogel Networks: PEG, PVA & smart hydrogels

5. Clinical Domains: Bone cements, drug release & tissue engineering

Lecture Aim

To evaluate biological, chemical, and physical performance requirements for polymer medical binders, comparing natural vs. synthetic matrix classes across implantable devices, tissue engineering, and drug delivery platforms.

Key Learning Tasks

Define: ISO 10993 cytotoxicity & hemocompatibility

Compare: Enzymatic vs. hydrolytic biodegradation

Analyze: PMMA bone cement polymerization

Assess: Sterilization impact on polymer integrity

Medical Paradigm: Polymer binders used in living organisms must fulfill strict non-toxicity requirements while providing structural support during tissue healing.


Function of Polymer Binders in Medicine

Medical binders function as matrix carriers, structural fixatives, bio-adhesives, and 3D cellular growth scaffolds.

Prosthetic Fixation
Anchor orthopedic metallic implants directly into trabecular bone tissue (e.g., PMMA bone cement).

Extracellular Matrix (ECM) Mimicry
Provide hydrated micro-environmental networks promoting cell attachment, migration, and differentiation.

Controlled Therapeutic Release
Entrap pharmaceutical drugs or growth factors within degrading polymer networks for sustained delivery.



Clinical Criteria: Non-mutagenic, non-pyrogenic, bio-absorbable without toxic degradation residues.

Primary Requirement: Biocompatibility (ISO 10993)

Non-Cytotoxicity

ISO 10993-5 Standard

Extracts from the polymer binder must not induce cell lysis, membrane damage, or metabolic inhibition.

Hemocompatibility

ISO 10993-4 Standard

Must not trigger hemolysis, platelet activation, or thrombus formation upon blood contact.

Non-Immunogenicity

ISO 10993-10 / 11

Zero chronic inflammatory or foreign-body giant cell response at the implant bed.

Key Testing Metric: MTT cell viability assay score must exceed 80% relative to control blanks.

Requirement: Controlled Biodegradation

Matching Regeneration Rate

The rate of binder bio-absorption must match the velocity of neo-tissue ingrowth, ensuring structural load is transferred smoothly to host tissue.

> **Nontoxic Degradation Byproducts**
> Degradation species (e.g., lactic acid, monomeric sugars) must be metabolized via natural biochemical pathways (Krebs cycle).

Degradation Timeline

Tunable range depending on clinical indication (wound vs bone repair).

pH Stability Goal: Local tissue pH must remain within physiological bounds (7.2 – 7.4) during erosion.

Requirement: Sterilization Stability

Gamma / E-Beam Irradiation

Risk: Free-radical generation alters degradation kinetics. Dose of 25 kGy. Can trigger polymer chain scission in PLA/PGA, drastically shortening mechanical half-life.

Ethylene Oxide Gas (EtO)

Constraint: Requires long outgassing times to remove toxic residual EtO gas. Low-temperature chemical method suited for heat-sensitive polymers.

Steam Autoclaving

Limitation: Deforms polymers with Tg or Tm below 130°C (e.g., PCL, PLA). 121°C at 15 psi pressure.

Sterility Assurance Level (SAL): Binder processing must achieve SAL of 10^{-6} without altering mechanical performance.

Natural Binders: Collagen & Gelatin

Type I Collagen Structure

Triple-helical protein containing RGD (Arg-Gly-Asp) peptide sequences that interact directly with integrin receptors on cell membranes.

> **Gelatin (Denatured Collagen)**
> Thermally denatured product with lower antigenicity, high solubility, and excellent hydrogel-forming capacity.

Crosslinking Stabilization

- Glutaraldehyde (chemical crosslinker)
- Genipin (natural low-toxicity agent)
- Enzymatic degradation via collagenases

Clinical Role: Hemostatic sponges, skin graft substitutes, and bone tissue scaffolds.

Natural Polysaccharide Binders: Chitosan & Alginate

Chitosan (Cationic)

Deacetylated Chitin Derivative

- Protonated amine (-NH3+) groups interact with bacterial cell walls (intrinsic antibacterial efficacy).
- Promotes rapid blood clotting via erythrocyte aggregation.
- Degrades in vivo via lysozyme enzymatic cleavage.

Alginate (Anionic)

Marine Brown Algae Extract

- Linear co-polymer of β-D-mannuronic (M) and α-L-guluronic (G) acids.
- Instant ionic crosslinking with divalent Ca2+ ions forming "egg-box" hydrogels.
- Widely used for cell encapsulation and wound dressings.

Polyelectrolyte Complexes: Mixing chitosan and alginate yields stable electrostatic coacervate hydrogels.

Synthetic Polyesters: PLA & PGA

Polylactic Acid (PLA)

Degradation Time: 12 to 24 months (slow bulk erosion).

PLLA / PDLA Enantiomers

Hydrophobic polymer with high mechanical strength. Hydrolytic degradation yields L-lactic acid, converted to CO_2 via Krebs cycle.

Polyglycolic Acid (PGA)

Degradation Time: 4 to 6 weeks (rapid strength loss).

Highly Crystalline Polyester

Rapid hydrolytic cleavage due to lack of pendant methyl groups. High initial modulus ($E \approx 6.5$ GPa).

Degradation Mechanism: Random ester cleavage via bulk hydrolysis; requires monitoring of local acid buildup.

Tunable Synthetic Binders: PLGA & PCL

Tailored Degradation

PLGA: Monomer Ratio Tailoring

Poly(lactic-co-glycolic acid) copolymer degradation is tuned by varying LA:GA ratios. PLGA 50:50 exhibits the fastest degradation rate (~1 month) due to amorphous structure.

Polycaprolactone (PCL)

Semi-crystalline polyester with low melting point (Tm ≈ 60°C). Highly ductile, degrading slowly over 2–3 years. Ideal for 3D bioprinting.

FDA Approval Status: PLGA and PCL are fully FDA-approved for human surgical implants and drug delivery vehicles.

Acrylic Binders: PMMA Bone Cement Systems

Two-Component System

Mixing: Free-radical polymerization yields dough-like moldable cement.

Powder: PMMA prepolymer beads + Benzoyl Peroxide (BPO) initiator + $BaSO_4$ radiopacifier.

Liquid: MMA monomer + DMPT accelerator + Hydroquinone stabilizer.

Clinical Limitations

Exothermic Curing: Reaction temperatures reach 70–90°C, risking thermal bone necrosis.

Monotoxicity: Unreacted MMA monomer exhibits systemic cytotoxicity.

High Modulus Mismatch: Stiffness causes stress shielding.

Primary Use: Fixation of total hip and knee joint prostheses in orthopedic surgery.

Synthetic Hydrogel Matrices: PEG, PVA, & pHEMA

Hydrated Polymer Binders

Polyethylene Glycol (PEG)
Stealth & Non-Fouling

Resists non-specific protein adsorption. Photocrosslinkable PEGDA hydrogels serve as cell scaffolds.

Polyvinyl Alcohol (PVA)
Cryogelation Processing

Formed via physical freeze-thaw thermal cycling, creating rubbery hydrogels for artificial cartilage replacements.

Poly(HEMA)
Optical Transparency

Flexible, oxygen-permeable hydrogel binder used in soft contact lenses and intraocular implants.

Water Content Range: Hydrogel matrices absorb **40% to 98% water by weight**, closely mimicking soft human tissue hydration.

Smart & Stimuli-Responsive Binders

Environment-Sensitive Polymers

Thermo-Responsive: PNIPAAm

Poly(N-isopropylacrylamide) exhibits a Lower Critical Solution Temperature (LCST) at 32°C. Soluble at room temperature, it phase-separates into an in-situ hydrogel binder at physiological body temperature (37°C).

pH-Responsive Binders

Polymers containing weak acid (PMAA) or base (PDEAEMA) groups collapse or swell in response to tumor/ischemic tissue acidosis (pH 6.5–6.8).

In-Situ Gelling

Injectable liquid precursors solidify inside irregular anatomical defects without surgical incision.

Clinical Utility: Minimally invasive delivery of therapeutics directly into target tissue sites.

Mechanical Matching & Stress Shielding

The Stress Shielding Problem

Result: High failure rate of rigid non-compliant implants.

If an implant binder possesses a modulus far higher than host tissue (e.g., Titanium E = 110 GPa vs. Cortical Bone E = 18 GPa), the implant carries all load. Bone remodels according to Wolff's law and resorbs, causing implant loosening.

Polymer Matrix Compliance Solution

Polymer binders (PEEK E = 3.8 GPa; composite PEEK-HA E = 12 GPa) can be matched to native bone tissue stiffness.

- Restores natural stress distribution.
- Stimulates healthy osteoblast bone formation.

Biomechanical Requirement: Match both elastic modulus and viscoelastic loss tangent (tan δ).

Erosion Mechanics: Bulk vs. Surface Erosion

Bulk Erosion (PLA, PGA, PLGA)

Water Diffusion > Hydrolysis Rate

- Water rapidly penetrates whole polymer interior.
- Molecular weight declines throughout entire volume simultaneously.
- Structural failure occurs suddenly before total mass loss.

Surface Erosion (Polyanhydrides)

Hydrolysis Rate > Water Diffusion

- Polymer degrades strictly from outer surface inward like a bar of soap.
- Device dimensions shrink predictably while core remains intact.
- Enables zero-order constant drug release kinetics.

Critical Parameter: Ratio of hydrolysis rate constant to water diffusion coefficient (D).

Medical Bio-Adhesives & Surgical Sealants

Cyanoacrylates (n-BCA, OCA)
Instant Anionic Polymerization

Polymerizes in seconds upon contact with moisture on skin surfaces for sutureless topical wound closure.

Fibrin Sealants
Enzymatic Clot Mimicry

Human fibrinogen + thrombin blend forming instant hemostatic fibrin networks in vascular surgery.

PEG-NHS Ester Hydrogels
Covalent Amine Coupling

Synthetic sealant (CoSeal, DuraSeal) bonding covalently to tissue amine groups to prevent CSF leaks.

Wet Adhesion Challenge: Polymer adhesives must displace water and form strong surface bonds in aqueous biological environments.

Polymer Binders in Dental Medicine

Photopolymerizable Resin Matrices

Bis-GMA (Bisphenol A glycidyl methacrylate) and UDMA (Urethane dimethacrylate) blended with low-viscosity TEGDMA diluents.

> **Photo-Initiation System**
> Camphorquinone (CQ) + tertiary amine accelerator photo-cured via blue LED light (λ = 468 nm).

Glass Ionomer Cements

Polyacrylic acid binder reacting with fluoroaluminosilicate glass, releasing fluoride ions to prevent secondary caries.

Biological Requirement: Low monomer leaching to prevent pulp tissue irritation.

Binders for Controlled Drug Delivery

Diffusion-Controlled Systems

Example: Subdermal contraceptive implants (Norplant).

Active pharmaceutical ingredients (APIs) disperse within non-degradable polymer matrices (Silicone, EVAc). Release kinetics governed by Fick's first law of diffusion.

Erosion-Controlled Systems

Example: Lupron Depot (sustained peptide delivery).

Drug release rate is directly coupled to hydrolytic cleavage of bio-erodible polymer matrix bonds (PLGA micro-particles, polyanhydrides).

Therapeutic Advantage: Maintains plasma drug concentrations strictly within the therapeutic window, avoiding toxic peak spikes.

Polymer Hydrogel Binders in 3D Bioprinting

Bio-Ink Rheological Requirements

Hydrogel binders must present shear-thinning flow behavior under extrusion nozzle shear stress, followed by instantaneous shape recovery (yield stress) post-printing.

GelMA (Gelatin Methacryloyl)

Gold standard bio-ink binder photocrosslinked via UV/visible light in the presence of LAP photoinitiator, maintaining cell viability > 90%.

Crosslinking Mechanisms: UV light, ionic Ca2+ addition, or enzymatic (transglutaminase) crosslinking.

Regulatory Evaluation & Approval Pathways

Class I Devices
Low Risk

External contact materials (bandages, compression binders). Subject to general controls.

Class II Devices (510k)
Moderate Risk

Absorbable sutures, dental composites. Requires demonstration of substantial equivalence to predicate device.

Class III Devices (PMA)
High Risk / Life Sustaining

Implantable tissue scaffolds, drug-eluting vascular binders. Requires full clinical trials and Premarket Approval (PMA).

Master Files: Polymer suppliers maintain FDA Device Master Files (DMF) to document material synthesis purity.

Natural vs. Synthetic Binders: Clinical Trade-offs

Natural Binders

Pros: Intrinsic bioactivity, cell recognition RGD sequences, non-toxic enzymatic degradation.

Cons: Batch-to-batch variation, immunogenicity risk, rapid degradation, low mechanical strength.

Synthetic Binders

Pros: Reproducible industrial synthesis, predictable mechanical properties, tunable degradation rate.

Cons: Lack cell-adhesive ligands, potential acidic degradation byproducts, hydrophobic surface.

Hybrid Solution: Combining synthetic polymer backbones with functionalized bioactive natural peptide sequences.

Toxicological Risk Assessment of Medical Binders

Residual Monomers

Unreacted MMA or ethylene oxide leads to localized tissue necrosis. Monomer leaching must remain <0.5%.

Catalyst & Initiator Residuals

Heavy metals (tin octoate used in PLA synthesis) must be extracted to prevent long-term organ accumulation.

Particulate Debris

Wear micro-particles (<10 μm) induce macrophage phagocytosis, osteolysis, and implant failure.

Analytical Screening: GC-MS and ICP-MS testing required to quantify extractable leachables.

Future Horizons in Medical Binders

Gene-Activated Smart Matrices

Polymer binders non-covalently complexed with plasmid DNA or siRNA vectors, transfecting migrating host cells in real-time to induce tissue regeneration.

Conductive Binders: PEDOT:PSS hydrogels providing electrical stimulation for neural repair.

Living Bio-Binders: Engineered bacterial cellulose matrices with dynamic self-healing capacity.

Shape Memory Polymers: Self-expanding vascular stents deployed via micro-catheters.

Clinical Vision: Biomimetic matrices that achieve full functional tissue integration without scarring.

Summary: Key Medical Binder Requirements

01

Biological Safety

Strict compliance with ISO 10993 cytotoxicity, hemocompatibility, and non-pyrogenicity standards.

02

Predictable Kinetics

Tunable hydrolytic/enzymatic degradation yielding non-toxic excretable metabolic byproducts.

03

Biomechanical Compliance

Matching matrix modulus and toughness to target native tissues to eliminate stress shielding.

Core Takeaway: The ideal medical binder balances bio-functionality, mechanical integrity, structural safety, and regulatory compliance.

Thank You for Your Attention

acc.professor Kudaibergenova Bates Malikovna.